

Amendments to the Claims

1. (Currently amended) A porous hollow fiber, comprising a stretched single layer of a vinylidene fluoride resin having a weight-average molecular weight of at least 3×10^5 , having a water permeation rate F ($\text{m}^3/\text{m}^2 \cdot \text{day}$) measured at a pressure difference of 100 kPa and at a water temperature of 25°C in a range of test length $L=0.2-0.8(\text{m})$ and expressed in a linear relationship with the test length L of: $F=C \cdot L+F_0$ (formula 1) and satisfying requirements (a)-(d) shown below:

(a) ~~a~~ an average slope C (/day) of: $-20 \leq C \leq 0$,

(b) an intercept (basic permeability) F_0 ($\text{m}^3/\text{m}^2 \cdot \text{day}$) of: $F_0 \geq 30$,

(c) a relation between F_0 ($\text{m}^3/\text{m}^2 \cdot \text{day}$) and an average pore diameter P (μm) according to half-dry method of $F_0/P \geq 300$, and

(d) an outer diameter of at most 3 mm;

wherein the vinylidene fluoride resin comprises 2-49 wt.% of a first vinylidene fluoride resin having a weight-average molecular weight (Mw_1) of 4×10^5 - 12×10^5 and 51-98 wt.% of a second vinylidene fluoride resin having a weight-average molecular weight (Mw_2) of 1.5×10^5 - 6×10^5 provided that the weight-average molecular weight (Mw_1) of the first vinylidene fluoride resin and the weight-average molecular weight (Mw_2) of the second vinylidene fluoride resin satisfy a ratio Mw_1/Mw_2 of at least 1.2.

2. (Original) A porous hollow fiber according to claim 1, further satisfying a relationship of : $F_0/D_i^4 \leq 75$ between the basic permeability F_0 ($\text{m}^3/\text{m}^2 \cdot \text{day}$) and an inner diameter D_i (mm) of the hollow fiber.

3. (Previously presented) A porous hollow fiber according to claim 1, comprising a vinylidene fluoride resin having a weight-average molecular weight of at least 4×10^5 .

4. (Previously presented) A porous hollow fiber according to claim 1, comprising a vinylidene fluoride resin having a ratio Mw/Mn of at least 2.0 between a weight-average molecular weight (Mw) and a number-average molecular weight (Mn) thereof.

5. (Cancelled)

6. (Previously presented) A porous hollow fiber according to claim 1, having an inner diameter of 0.8-2.98 mm and a wall thickness of 0.01-0.4 mm.

7. (Currently amended) A process for producing a porous hollow fiber of vinylidene fluoride resin according to claim 1, comprising : providing a composition by adding, to 100 wt. parts of a vinylidene fluoride resin having a weight-average molecular weight of at least 3×10^5 , a plasticizer and a good solvent for vinylidene fluoride resin in a total amount of 100-300 wt. parts so that the good solvent occupies 8-22 wt.% therein ; melt-extruding the composition into a form of hollow fiber; introducing the hollow fiber into an inert liquid while injecting an inert gas into a hollow part thereof to cool and solidify the hollow fiber; ~~and~~ extracting the plasticizer to recover a porous hollow fiber; and stretching the hollow fiber before or after the extraction of the plasticizer,

wherein the vinylidene fluoride resin comprises 2-49 wt.% of a first vinylidene fluoride resin having a weight-average molecular weight (Mw1) of 4×10^5 - 12×10^5 and 51-98 wt.% of a second vinylidene fluoride resin having a weight-average molecular weight (Mw2) of 1.5×10^5 - 6×10^5 provided that the weight-average molecular weight (Mw1) of the first vinylidene fluoride resin and the weight-average molecular weight (Mw2) of the second vinylidene fluoride resin satisfy a ratio Mw1/Mw2 of at least 1.2.

8. (Cancelled)